

bercoweld[®]

wire solutions for brazing and welding

bedra
intelligent wires

Filler metals for brazing and welding made of copper and copper alloys

bercoweld® from bedra.

With a tradition spanning more than 120 years, bedra has become synonymous with innovative high-tech precision wires made in Germany. We serve customers around the world in the brazing and welding technology as well as EDM, electronics and specialty applications from our two German factories.

With **bercoweld®** we have developed wire electrodes especially designed for the brazing and welding technology industries.

We are the only manufacturer of precision wires to offer the entire production chain - from melting to final packaging - from a single source.

The established bedra in-house concept also includes our own foundry. It goes without saying that only virgin metals are used for the production of **bercoweld®**.

Thus, bedra customers will acquire wire electrodes of outstanding quality ensuring reliable processing and complete traceability.

You can rely on it

Strict quality assurance guarantees the reliability of our products: bedra precision wires are produced under a certified QM system acc. to DIN EN ISO 9001:2008.

Our Environmental Management System is certified acc. to DIN EN ISO 14001:2004.



■ In the bedra own foundry, **bercoweld®** wires are produced while adhering to tightest alloy tolerances



- Your benefits at a glance:
- Material closure joints
 - Good gap bridging
 - High corrosion resistance



■ Automotive industry



■ Rail vehicles



■ Plant engineering

Some examples of the wide range of **bercoweld®** applications.

bercoweld® in detail

The appropriate product for every application: Our **bercoweld®** range currently comprises more than 20 alloys of the following material groups

- low-alloyed copper alloys
- tin-bronzes
- aluminium-bronzes
- copper-nickel-alloys
- special alloys

bercoweld® in application

Be it MIG/MAG brazing or welding, TIG welding, laser and plasma brazing or flame spraying: **bercoweld®** wire electrodes are as varied as their range of applications, be it in the automotive industry, track and railroad car construction, plant engineering, offshore or onshore, **bercoweld®** is always an integral part of innovative joining technologies.

bercoweld® on the move

The automotive sector represents a major application area for **bercoweld®**. Applications such as tailormade body blanks of thin sheets in different qualities are laser-welded, low or high-temperature brazed with **bercoweld®**.

All renowned automobile manufacturers worldwide rely on **bercoweld®** wire electrodes from bedra.

Product range

Calculation of running length (as an example for the bercoweld® alloys S3 and A8):

Wire diameter in mm	Density kg/dm ³	15 kg spool				200 kg drum/wooden spool		
		0,8	1	1,2	1,6	1	1,2	1,6
Product	Density kg/dm ³	approx. wire length in meter				approx. wire length in meter		
S3	8,5	3.515	2.248	1.564	878	29.974	20.815	11.709
A8	7,7	3.877	2.482	1.723	969	33.088	22.978	12.925



Material	bedra alloy	Standard designation	Composition (weight %)									Physical properties of the materials						Mechanical properties of the weld joint, standard data				Product details & applications					
			Cu	Al	Si	Sn	Mn	Ni	P	Fe	Others	Density kg / dm ³	Melting range °C	Thermal conductivity W/m · K	Coefficient of thermal expansion 10 ⁻⁶ /K	Electric conductivity S · m/mm ²	IACS %	Tensile strength N/mm ²	Elongation %	Brinell hardness HB 2.5 / 62.5	Notched bar impact test Av(7)						
Low alloyed copper materials	bercoweld K3 (SF-Cu)	not standardized	balance									0.05					8.9	~ 1080	293-364	17.0	41-52	~70-89	220	40	50	65	Oxygen-free special copper wire. Joining of grey cast iron and steel, copper-to-copper joining.
	bercoweld K5 (CSSM)	Cu1898 (ISO 24373) SG-CuSn (DIN 1733) ERCu (AWS A5.7-84)	balance		0.2	0.8	0.2						0.01	max. 0.5			8.9	1020-1050	120-145	18.1	15-20	~26-34	220	30	60	75	Sn-alloyed copper wire. Especially suited for joining and overlay welding on copper; joining of grey cast iron and steels possible, joining of zinc-coated sheets.
	bercoweld S3 (CuSi3Mn)	Cu6560 (ISO 24373) SG-CuSi3 (DIN 1733) ERCuSi-A (AWS A5.7-84)	balance		2.9		0.9								max. 0.5		8.5	965-1035	35	18.1	3.5-4.0	~6-7	350	40	80	60	Zinc-coated car body sheets in the automotive industry, overlay welding on low-alloyed steels, solenoid valves, control cabinets.
	bercoweld S2 (COMAS)	Cu6511 (ISO 24373)	balance		1.8	0.2	1.0						0.01				8.7	1030-1050	40	18.1	4.7-5.3	~8-9	285	45	62	75	Specifically developed material with reduced Si-content for brazing of zinc-coated sheets, better flowing properties than S3.
Tin bronzes	bercoweld K8/K9 (CuAg/WG)	Cu1897 (ISO 24373) SG-CuAg (DIN 1733)	balance					0.1					0.01	max. 0.5			8.9	1070-1080	220-315	17.7	44-46	~70-80	200	30	60	75	Copper-silver material. Particularly suitable for joining and overlay welding on copper; for large workpieces preheating to approx. 450°C is recommended.
	bercoweld B6 (B166)	Cu5180 (ISO 24373) SG-CuSn6 (DIN 1733) ERCuSn-A (AWS A5.7-84)	balance			6.5						0.25		max. 0.5			8.7	910-1040	75	18.1	6-7	~10-12	260	20	80	32	Repairs to large copper parts or bronzes, furnace soldering, solenoid valves, heat exchangers, slide rails, bearing bushes.
	bercoweld B8 (B180)	Cu5210 (ISO 24373) SG-CuSn6 (DIN 1733) ERCuSn-C (AWS A5.6-84)	balance			8.0						0.1		max. 0.5			8.8	875-1025	67	18.5	6-8	~10-14	260	20	80	32	Repairs to bronzes. Furnace brazing, solenoid valves. Also suited for zinc-coated sheets, slide rails and bearing bushes.
	bercoweld B60 (BS60)	not standardized	balance		0.25	6.0	0.25							max. 0.5			8.8	900-1040	62	18.4	7.3-7.9	~12-14	359	44	101	68	Specifically developed alloy for zinc-coated sheets in the automotive industry.
Aluminium bronzes	bercoweld B10 (BS100)	Cu5211 (ISO 24373)	balance		0.25	9.5	0.25							max. 0.5			8.7	887-1020	47	18.0	5-6	~9-10	290	14	115	24	Specifically developed alloy for zinc-coated sheets in the automotive industry.
	bercoweld B12 (B130)	Cu5410 (ISO 24373)	balance			13.0						0.2		max. 0.5			8.6	825-990	40-50	18.5	3-5	~5-9	320	5	120	8	Welding of copper materials of any kind. Overlay welding on bearing bushes, slide rails. Highest hardness for bronzes.
	bercoweld A52 (AlBz5Ni2)	Cu6061 (ISO 24373)	balance	5.0			0.2	2.0						max. 0.5			8.2	1060-1085	61	17.5	8-8.8	~14-15	353	45	84	161	Specifically developed alloy for joining zinc-coated sheets and ferritic steels. Solenoid valves, shipbuilding, container, railroad car construction.
	bercoweld A8 (AlBz8)	Cu6100 (ISO 24373) SG-CuAl8 (DIN 1733) ERCuAl-A1 (AWS A5.7-84)	balance	8.0										max. 0.5			7.7	1030-1040	65	17.0	7-9	~12-15	430	40	100	100	Standard alloy for zinc-coated sheets and ferritic steels. Solenoid valves, joining and overlay welding on aluminium bronzes.
Copper-nickel alloys	bercoweld A822 (AlBz8MNF)	Cu6327 (ISO 24373) SG-CuAl8Ni2 (DIN 1733)	balance	8.0			2.0	2.0		2.0				max. 0.5			7.5	1030-1050	50	17.0	4.5-5.5	~8-9	530	30	140	70	Seawater and corrosion resistant. Joining and overlay welding on aluminium bronzes. Solenoid valves, shipbuilding, grey cast iron, zinc-coated steels, bearing surfaces, bearing parts, fittings, pump housings.
	bercoweld A9 (AlBz9Fe)	Cu6180 (ISO 24373) SG-CuAl10Fe (DIN 1733) ERCuAl-A2 (AWS A5.7-84)	balance	9.5							1.2			max. 0.5			7.6	1030-1040	55	16,5	6.5-7.5	~11-13	500	35	140	95	Seawater and corrosion resistant. Joining and overlay welding on aluminium bronzes. Also suitable for zinc-coated sheets, solenoid valves, shipbuilding, bearing surfaces, bearing housings.
	bercoweld A922 (AlBz9Ni)	Cu6327 (ISO 24373) SG-CuAl8Ni2 (DIN 1733)	balance	9.0			2.0	2.5		1.5				max. 0.5			7.5	1030-1050	50	17.0	4.5-5.5	~8-9	530	30	150	70	Seawater and corrosion resistant. Joining and overlay welding on aluminium bronzes. Solenoid valves, shipbuilding, grey cast iron, zinc-coated steels, bearing surfaces, bearing parts, fittings, pump housings.
	bercoweld A35 (AlBz35)	Cu6328 (ISO 24373) SG-CuAl9Ni5 (DIN 1733) ERCuNiAl (AWS A5.7-84)	balance	9.0			1.5	5.0		3.5				max. 0.5			7.5	1015-1045	20-40	19.3	3-4	~5-7	690	16	min. 200	68	High-strength alloy. Seawater, wear and abrasion resistant. Resistant to cavitation and erosion. Joining and overlay welding on aluminium bronzes. Particularly suited for ship propellers, slide rails, valve gear housings.
	bercoweld A300 (MAXAL300)	Cu6331 (ISO 24373) SG-CuMn13Al7 (DIN 1733) ERCuMnNiAl (AWS A5.7-84)	balance	8.0			13.0	2.5		2.5				max. 0.5			7.4	945-985	30	21.5	3-5	~5-9	900	10	290	180	High-strength alloy, spark discharge resistant. Seawater, wear and abrasion resistant. Resistant to cavitation and erosion. Joining and overlay welding on aluminium bronzes. Particularly suitable for ship propellers, slide rails, valve gear housings.
	bercoweld N10 (CuNi10Fe)	Cu7061 (ISO 24373) SG-CuNi10Fe (DIN 1733)	balance				1.0	10.5		1.5		max. 0.5	Ti 0.4				8.9	1100-1145	30	17.0	2.8-3.2	~5-6	300	34	80	190	Particularly suitable for joining and overlay welding of CuNi materials having a nickel content of max. 30 %. Corrosion resistant. Shipbuilding, pipelines, chemical industry.
bercoweld N30 (CuNi30Fe)	Cu7158 (ISO 24373) SG-CuNi30Fe (DIN 1733) ERCuNi (AWS A5.7-84)	balance				1.0	31.0		0.5		max. 0.5	Ti 0.4				8.9	1180-1240	30	17.3	2.7-3.3	~5-6	420	36	115	240	Particularly suitable for joining and overlay welding of CuNi materials having a nickel content of max. 30 %. Corrosion resistant. Shipbuilding, pipelines, chemical industry. Yet higher resistance to attacks of any kind.	
Special alloys	bercoweld K1 (E-Cu58)	not standardized	99.90											max.0,1			8.93	1083	394	17.3	58.6	100	200	40	50	60	Oxygen-containing copper alloy, particularly suited for joining and overlay welding on copper.
	bercoweld K2 (OF-Cu)	not standardized	99.99											max.0.01			8.93	1083	394	17.3	58.6	100	200	40	50	60	Oxygen-free copper alloy, particularly suited for joining and overlay welding on copper, furnace soldering, shaped solder pads.
	bercoweld M122 (CuMn12Ni2)	not standardized	balance				12	2						max.0.5			8.4	950-970	22	18.3	2.2-2.4	~3-4	400	40	100	100	Special alloy for solenoid valves. Also suitable for zinc-coated sheets.

Innovative bedradox!



Opt for **bercoweld**® supplied in the innovative bedradox! Due to a high filling capacity and continuous wire pay-off, time-consuming spool changes are a thing of the past and downtimes in production are significantly reduced.

Technical data	
Width	510 mm
Height without hood	790 mm
with hood	1160 mm
with hood and pallet	1300 mm
Filling weight max	max. 200 kg
Alloys	upon request
Dimensions	0,80 - 1,60 mm





And, needless to say, the bedradox is made from recycled and recyclable cardboard. That's good for the environment and good for you as the bedradox can easily be returned into the raw material cycle.

Realize cost reductions when joining zinc-coated sheets

The German automotive industry has successfully led the way in joining zinc coated sheets with copper wire without extensive reworking. Subsequent processing and zinc coating of the joint is no longer necessary, while corrosion protection is still maintained. As a result, significant time and cost savings have been realized.

Advantages of brazing with copper alloys

- excellent gap bridging
- low joining temperature
- low energy requirement
- due to lower temperature lower distortion of the basic material
- no zinc coating of the joint necessary




Applications


- steel construction
- apparatus engineering
- shipbuilding
- furniture
- control cabinet
- ventilation shafts
- facades
- stairs
- sunrooms
- fences
- barriers
- building industry
- recycling systems
- truck trailer
- vehicle construction
- balcony
- carports
- store construction
- machine building
- gates
- container
- utility vehicle construction
- scales
- feed systems

bercoweld®

Overview spools



Type	Material	Volume (kg)	Flange a (mm)	Core b (mm)	Bore c (mm)	Interior size d (mm)	Exterior size e (mm)
SD300	plastic	12-15	300	212	51,5	91	103
BS300	steel	12-15	300	189	52	92	100
K300	steel	12-15	300	198	adaptor	90	98
H500	wood	max. 150	500	250	127	270	320
H560	wood	max. 200	560	200	127	260	320
H760	wood	max. 300	760	360	40	240	290



wire diameter: from 0,80 to 2,40 mm. Further dimensions on request.

Further packagings

Drums

Wire diameter: from 0,80 mm to 1,60 mm

Filling weight: 200 kg (max.)

Accessories: plastic hood, hose pack, pay-off device

Further dimensions on request.

Coils

Wire diameter: from 1,60 mm to 6,00 mm

Weight: from 25 to 100 kg

Outer diameter: from 450 to 600 mm

Inner diameter: from 350 to 450 mm

Further dimensions on request.

Rods

Wire diameter: from 1,60 mm to 6,00 mm

Length: from 250 mm to 3000 mm

Cut without burrs. Rod identification possible by flat stamping.

Further dimensions on request.

Packaging

Spools: Foil bags with silicagel in cardboard boxes

Rods: Cardboard boxes: 5 kg / 10 kg / 25 kg

Coils: Paper wrapping on request

Further packagings on request

Higher productivity with **bercoweld**® from the bedradox!

Optimize your welding and brazing processes!



bedra
intelligent wires

bercoweld®

Edition 02/2012. The contents of this brochure are protected by copyright. Copyright Berkenhoff GmbH. Subject to technical modifications and errors.

Berkenhoff GmbH
Berkenhoffstrasse 14
D-35452 Heuchelheim
www.bercoweld.com

Phone: +49 (0) 641 - 601 0
Fax: +49 (0) 641 - 601 212
e-mail: info@bedra.com

bedra
intelligent wires